



Spinel refractories
Technical data sheet
SPGUN55



General information						
Product properties		Average Value			limited values	
Classification		Medium Alumina				
Main raw material		Low Iron chamott				
Bonding type		Hydraulic				
Grain size		0-5mm				
Working method		gunning				
Bulk Density kg/m^3 ASTM C20		2200				
Liquid addition						
Storage limit		6month / Dry Condition				
Max Service Temp		1530°C				
CCS @ 1480 °C ASTM C133 (kg/cm^2)					450	800
CCS @ 110 °C ASTM C133 (kg/cm^2)					350	600
Linear Change%@110°C		Negligible				
Linear Change%@1480°C					-1.50	0.50
Modulus of Rupture@110°C (kg/cm^2)					60	100
Modulus of Rupture@1480°C (kg/cm^2)					70	100
Chemical analysis(Typical /Approximate)						
Al_2O_3 %	SiO_2 %	Fe_2O_3 %	TiO_2 %	MgO %	CaO %	SiC %
49-55	36-39	1-2	-	-	5.5-6.5	-